

# PRODUCT MATERIAL SPEC

## SF60

### Woven Geotextile

**MKB SF60** is a woven geotextile made up of high tenacity polypropylene yarns that are woven to form stable and durable structure, which allows the yarns to maintain their relative position. It is non-biodegradable and resistant to ultraviolet degradation, rotting, and most soil chemicals. **MKB SF60** conforms to the property values listed below.

PROPERTY	TEST METHOD	MARV English
Tensile Strength (Grab)	ASTM D4632	60 x 60 lbs
Elongation	ASTM D4632	15%
CBR Puncture	ASTM D6241	200 lbs
Trapezoidal Tear	ASTM D4533	30 x 30 lbs
UV Resistance (500 hrs)	ASTM D4355	70%
Apparent Opening Size (AOS)*	ASTM D4751	30 US Std. Sieve
Permittivity	ASTM D4491	0.05 sec <sup>-1</sup>

\*\*Maximum Average Roll Value

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.